

ABSTRACT

A monolayer film of a polymer blend of a first component selected from the group consisting of an ethylene containing polymer, the first component present in an amount by weight of the film from about 60% to about 1%, the first component having a first melting  
5 point temperature determined by DSC, a second component selected from the group consisting of propylene containing polymers and methyl pentene containing polymers, the second component being present in an amount by weight of the film from about 99% to about 40%, the second component having a second melting point temperature determined by DSC; and the film being capable of withstanding steam sterilization at a temperature from about  
10 100°C to about 130°C.